



AUTOMOTIVE METALLIC SPECK

DESCRIPTION AND USES

Rust-Oleum® Metallic Speck is designed to produce a bright metallic effect. Metallic Speck is recommended for automotive accessories, helmets, bikes, and more.

Rust-Oleum Metallic Speck features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCTS

SKU	Description
251598	Red (11 oz.)
251600	Blue (11 oz.)
252457	Silver (11 oz.)
252458	Gold(11 oz.)

PAINTING APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, and wax with Rust-Oleum® Wax & Tar Remover. Wash the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and dry with a clean cloth.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a Rust-Oleum Primer provides added corrosion protection on metal and promotes adhesion and hiding. A primer is especially recommended for metal and plastic surfaces. Recommended primers include 249321 Primer Sealer and any of the sandable primers (249419 Red, 252472 Light Gray or 249415 Gray).

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart. Maximum adhesion is achieved in 48 hours. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20-30 minutes, to handle in 1 hour and fully dry in 24 hours. Apply a second coat if necessary at any time.

CLEAN-UP

Wipe off tip when finished. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



TECHNICAL DATA

AUTOMOTIVE METALLIC SPECK

PHYSICAL PROPERTIES

		METALLIC SPECK
Resin Type		Modified Alkyd
Pigment Type		Proprietary
Solvents		Acetone and Aromatic Hydrocarbons
MIR		1.25 Max
Fill Weight		11 ounces
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50 μ)
Practical Coverage at Recommended DFT		8-10 sq.ft./can (0.70-0.9 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	24 hours
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.